






MADRAS DECORI

60x120 ± 9 mm Matt/Satin & Glossy/High Glossy

Gres Porcellanato Smaltato . Glazed Porcelain Tile . Grès Cérame Émaillé . Glasiertes Feinsteinzeug

CARATTERISTICA TECNICA TECHNICAL FEATURE CARACTÉRISTIQUE TECHNIQUE TECHNISCHE EIGENSCHAFT	NORMA NORM NORME NORM	VALORE RICHIESTO REQUIRED STANDARD VALEUR STANDARD STANDARDWERT	MADRAS <i>decori</i>	
			Matt	Glossy/High Glossy
 LUNGHEZZA E LARGHEZZA. LENGHT AND WIDTH. LONGUER ET LARGEUR. LÄNGE UND BREITE. RETTILINEITÀ SPIGOLI. STRAIGHTNESS OF SIDES. RECTITUDE DES ARETES. KANTENGERADHEIT. ORTOGONALITÀ. RECTANGULARITY. ORTHOGONALITE. RECHTWINKLIGKEIT. PLANARITÀ. FLATNESS. PLANEITE DE SURFACE. EBENFLÄCHIGKEIT. SPESSORE. THICKNESS. EPAISSEUR. STÄRKE.	UNI EN ISO 10545-2	± 2,0mm	CONFORME. CORRESPONDING. CONFORME. ENTSPRICHT DEN ANFORDERUNGEN.	
		± 0,8mm		
		± 1,5mm		
		± 1,8mm		
		± 0,5mm		
 ASSORBIMENTO D'ACQUA. WATER ABSORPTION. ABSORPTION D'EAU. WASSERAUFNAHME.	UNI EN ISO 10545-3	≤ 0,5%	< 0.4 %	
 RESISTENZA ALLA FLESSIONE (N/mm ²) FLEXURAL STRENGHT TEST (N/mm ²). RÉSISTANCE À LA FLEXION (N/mm ²). BIEGEFESTIGKEIT (N/mm ²). SFORZO DI ROTTURA (S). BREAKING STRENGTH (S). EFFORT DE RUPTURE (S). BRUCHKRAFT (S).	UNI EN ISO 10545-4	≥ 35 N/mm ²	CONFORME. CORRESPONDING. CONFORME. ENTSPRICHT DEN ANFORDERUNGEN.	
		S ≥ 1300 N (SPESSORE . THICKNESS . EPAISSEUR . DICKE ≥ 7,5 mm)	≥ 1600 N	
		S ≥ 700 N (SPESSORE . THICKNESS . EPAISSEUR . DICKE < 7,5 mm)	-	
 COEFFICIENTE DI DILATAZIONE TERMICA LINEARE. LINEAR THERMAL EXPANSION. COEFFICIENT DE DILATATION THERMIQUE LINÉAIRE. LINEARER THERMISCHER AUSDEHNUNGSKOEFFIZIENT.	UNI EN ISO 10545-8	NON RICHIESTO – NOT REQUIRED	α ≤ 7.1x10 ⁻⁶ °C	
 RESISTENZA AGLI SBALZI TERMICI. THERMAL SHOCK RESISTANCE. RESISTANCE AUX ÉCORTS DE TEMPÉRATURE. TEMPERATURWECHSELBESTÄNDIGKEIT.	UNI EN ISO 10545-9	NESSUNA ALTERAZIONE. NO ALTERATION. AUCUNE VARIATION. KEINE VERÄNDERUNG.	RESISTE. RESISTANT RÉSISTE. WIDERSTANDSFÄHIG	